

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
28 March 2002 (28.03.2002)

PCT

(10) International Publication Number
WO 02/24786 A2

- (51) International Patent Classification⁷: **C08G 75/00**
- (21) International Application Number: **PCT/EP01/11021**
- (22) International Filing Date:
24 September 2001 (24.09.2001)
- (25) Filing Language: **English**
- (26) Publication Language: **English**
- (30) Priority Data:
09/669,099 25 September 2000 (25.09.2000) **US**
- (71) Applicant (for all designated States except US): **ES-SILOR INTERNATIONAL COMPAGNIE GENERALE D'OPTIQUE** [FR/FR]; 147 rue de Paris, F-94227 CHARENTON cedex (FR).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **JALLOULI, Aref, Ben, Ahmed**, [TN/US]; 13433 104th Avenue N., LARGO, FL 33774 (US). **KEITA, Gabriel** [FR/US]; 394 Fountain View Circle, OLDSMAR, FL 34677 (US). **WEBER, Steve** [US/US]; 14045 Egmont Line, CLEARWATER, FL 33762 (US). **TURSHANI, Yassin** [US/US]; 8073 Somerset Drive, LARGO, FL 33773 (US).
- (81) Designated States (national): **AL, AG, AI, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KI, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.**
- (84) Designated States (regional): **ARIPO** patent (GI, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), **Eurasian** patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), **European** patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), **OAPI** patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**
— without international search report and to be republished upon receipt of that report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: **EPISULFIDE BASED POLYMERIZABLE COMPOSITION CATALYZED BY AN (ALKOXYPHENYL)PHOSPHINE, ARTICLES MADE THEREFROM AND PROCESS FOR MAKING SAME**

(57) Abstract: The room temperature polymerizable composition comprises at least one polymerizable monomer having at least one episulfide functionality and an effective amount of at least one (alkoxyphenyl)phosphine polymerization catalyst.

WO 02/24786 A2

EPISULFIDE BASED POLYMERIZABLE COMPOSITION CATALYZED BY AN (ALKOXYPHENYL)PHOSPHINE, ARTICLES MADE THEREFROM AND PROCESS FOR MAKING SAME

BACKGROUND OF THE INVENTION

(1) Field of the invention.

The present invention relates to polymerizable compositions, polymerized resins, and in particular fast curing compositions at room temperature as well as to a polymerization process for making such resin.

The polymerized compositions and the polymerization process of the invention are particularly useful for making transparent optical articles such as lenses, prisms, optical fibers, filters or for making different types of substrates, such as information recording substrates.

The polymerizable composition and the polymerization process of the invention are also specifically suited for making various coatings and in particular coatings for optical applications.

(2) Description of the prior art

Transparent plastic materials are widely used in the optical field and particularly in the ophthalmic field for their lightness, high impact resistance.

Optically transparent plastic materials having a high refractive index $n_D = 1.6$ or even higher have been developed recently which render it possible to manufacture optical articles such as lenses of lower thickness for an equivalent corrective power (optical power).

EP 0.921.417 discloses a polymerizable composition comprising a sulfur-containing compound having at least one episulfide functionality, a compound having one or more active hydrogen atoms in one molecule, at least one of the active hydrogen atoms being an active hydrogen atom other than hydrogen atom of SH group, and optionally a polymerization catalyst.

Among the cited polymerization catalysts are the phosphines. The disclosed phosphines include trialkylphosphines and tricycloalkylphosphines, triphenylphosphine, tribenzylphosphine, tri(alkylphenyl)phosphines, dialkyl and

dicycloalkylphenylphosphines, alkyl and cycloalkyldiphenylphosphines, and chlorodiphenylphosphine.

Document EP 0.942.027 discloses a polymerizable composition comprising a (thio)epoxy compound having at least one intramolecular disulfide bond and a polymerization catalyst. Among the numerous polymerization catalysts that can be used, trialkylphosphines and triarylphosphines are cited.

Unfortunately, the polymerization of these polymerizable compositions needs a long thermal polymerization cycle, generally between 8 hours to 17 or more in order to obtain fully polymerized articles.

10

SUMMARY OF THE INVENTION

Thus, the aim of the present invention is to provide polymerizable compositions for making optically transparent resins which are thermally polymerizable and preferably polymerizable at room temperature in a short time cycle.

A further object of the invention is to provide polymerizable compositions as above which result in polymerizable resins having a high refractive index of 1.6 or more, and preferably of 1.7 or more.

The invention also concerns a polymerization process for making optically transparent resins which necessitates shorter time than the prior art processes.


The invention further concerns optical articles such as lenses made of the resins resulting from the polymerization of the polymerizable compositions.

It has now been discovered that, by using an effective amount of an alkoxyphenylphosphine as part of the catalyst or preferably as the sole catalyst in polymerizable compositions including at least one episulfide monomer, it was possible to use very short polymerization cycles while still obtaining a

polymerized resin which is optically transparent and free of striations and having good mechanical, scratch and heat resistance properties.

According to the present invention, there is a risk provided thermally or room temperature polymerizable compositions for making optically transparent resins and comprising at least one polymerizable monomer having at least one episulfide functionality and an effective amount of a polymerization catalyst, comprising a phosphine having at least one alkoxyphenyl group. More specifically, the polymerization catalyst is selected from phosphines of formula (I) :

10



and mixtures thereof, in which R and R' are alkyl groups, x is an integer from 1 to 3, y is an integer from 1 to 3 and z is an integer from 0 to 2 with the proviso that $x+z=3$, t is 0, 1, 2 or 3.

Preferably, the catalyst consists solely in the (alkoxyphenyl)phosphine of formula (I) or a mixture of these phosphines.

DETAILED DESCRIPTION OF THE INVENTION AND PREFERRED EMBODIMENTS

20

The (alkoxyphenyl)phosphine catalyst of formula (I) may comprise 1 to 3 alkoxy phenyl groups (x is 1, 2 or 3). The preferred (alkoxyphenyl)phosphine catalysts of formula (I) are tris(alkoxyphenyl)phosphines (i.e. : $z=0$)

The alkoxyphenyl groups of the phosphines of formula (I) may be monoalkoxy, dialkoxy or trialkoxyphenyl groups.

Preferably, the alkoxyphenyl groups are mono and dialkoxy groups, most preferably monoalkoxy groups.

5 The alkyl radical R in the alkoxy groups OR is generally selected from C₁-C₆ alkyl groups, preferably C₁-C₄ alkyl groups. Most preferably, R is CH₃.

In mono alkoxyphenyl groups, the alkoxy group is usually in position 3 or 4 on the phenyl ring, preferably in position 4. In the dialkoxyphenyl group, the alkoxy groups are preferably in position 2 and 6 of the phenyl ring whereas
10 in trialkoxyphenyl groups, the alkoxy groups are preferably in position 2, 4 and 6 on the phenyl ring.

The alkyl radical R' is generally selected from C₁-C₆ alkyl groups, preferably C₁-C₄ alkyl groups, such as methyl, ethyl and propyl.

The most preferred phosphine catalysts are tris(monoalkoxy)phosphines.

15 Among the preferred alkoxyphenylphosphines of formula (I), there may be cited tris(3-methoxyphenyl)phosphine, tris(4-methoxyphenyl)phosphine, tris(2,6-dimethoxyphenyl)phosphine and tris(2,4,6-trimethoxy-phenyl)phosphine. The most preferred phosphine is tris(4-methoxyphenyl)phosphine which gives the best compromise between a fast
20 polymerization reaction and a non charring system.

The alkoxyphenylphosphine catalyst shall be used in the polymerizable compositions in an effective amount i.e. an amount sufficient to promote the polymerization, particularly the room temperature polymerization, of the composition.

25 The effective amount of phosphine catalysts will obviously depend upon the phosphine catalyst itself and the nature of the monomer or mixture of monomers of the composition in order to obtain a fast polymerization while avoiding charring of the system.


Generally, the phosphine catalyst will be present in amounts ranging, based on the total weight of the polymerizable monomers, from 5 to 1800 parts per million (ppm), preferably 100 to 800 ppm and more preferably 200 to 700 ppm.

5 Preferably, the phosphine catalyst is added to the monomer mixture as a solution in an appropriate solvent. Solvents that can be used are tetrahydrofuran (THF), chloroform, water, N-methyl-2-pyrrolidone (NMP) and N, N-dimethylacetamide (DMAC). Preferred solvents are THF, NMP and DMAC.

The polymerizable episulfide monomers of the invention have at least
10 one episulfide functionality and preferably two ore more episulfide functionalities per molecule.


Preferably, the polymerizable monomers having at least one episulfide functionality are compounds having one or more episulfide structures represented by the following formula (II) in one molecule :

15



In which R¹ represents a hydrocarbon group having 1 to 10 carbon
20 atoms, R², R³ and R⁴ each represents an hydrogen atom or a hydrocarbon group having 1 to 10 carbon atoms, X represents S or O with the proviso that in the molecule the average number of S represented by X is about 50% of the total number of S and O constituting the three membered ring.

A preferred class of polymerizable episulfide monomer is represented by
25 compound of formula (III) :



in which R^5 , R^6 , R^7 , R^8 , R^9 and R^{10} each represents an hydrogen atom or
 a hydrocarbon group having 1 to 10 carbon atoms, X represents S or O with the
 proviso that, in the molecule, the average number of S represented by X is about
 50% or more of the total number of S and O constituting the three member
 rings, m represents an integer from 0 to 6 and n represents an integer from 0 to
 4.

Preferably, R^1 in formula (II) represents a methylene group or ethylene
 group and R^2 , R^3 and R^4 in formula (II) and R^5 , R^6 , R^7 , R^8 , R^9 and R^{10} in
 formula (III) each preferably represents a hydrogen atom or a methyl group. It
 is more preferable that R^1 represents a methylene group and R^2 , R^3 , R^4 , R^5 , R^6 ,
 R^7 , R^8 , R^9 and R^{10} each represents a hydrogen atom.

The average number of S in each of formula (II) and formula (III) is 50%
 or more, preferably 90% or more, more preferably 95% or more and more
 preferably substantially 100% of the total number of S and O constituting the
 three member rings.


Examples of these compounds include linear organic compounds such as
 bis(β -epithiopropylthio)methane, 1,2-bis(β -epithiopropylthio)ethane, 1,3-bis(β -
 epithiopropylthio)propane, 1,2-bis(β -epithiopropylthio)propane, 1-(β -epithio
 propylthio)-2-(β -epithiopropylthiomethyl)propane, 1,4-bis(β -epithiopropyl
 thio)butane, 1,3-bis(β -epithiopropylthio)butane, 1-(β -epithiopropylthio)-3-(β -
 epithiopropylthiomethyl)butane, 1,5-bis(β -epithiopropylthio)pentane, 1-(β -
 epithiopropylthio)-4-(β -epithiopropylthiomethyl)pentane, 1,6-bis(β -epithio
 propylthio)hexane, 1-(β -epithiopropylthio)-5-(β -epithiopropylthiomethyl)
 hexane, 1-(β -epithiopropylthio)-2-[(2- β -epithiopropylthioethyl)thio]ethane

and 1-(β -epithiopropylthio)-2-[[2-(2- β -epithiopropylthioethyl)thioethyl]thio]ethane ; branched organic compounds such as tetrakis(β -epithiopropylthiomethyl)methane, 1,1,1-tris(β -epithiopropylthiomethyl)propane, 1,5-bis(β -epithiopropylthio)-2-(β -epithiopropylthiomethyl)-3-thiapentane, 1,5-bis(β -epithiopropylthio)-2,4-bis(β -epithiopropylthiomethyl)-3-thiapentane, 1-(β -epithiopropylthio)-2,2-bis(β -epithiopropylthiomethyl)-4-thiahexane, 1,5,6-tris(β -epithiopropylthio)-4-(β -epithiopropylthiomethyl)-3-thiahexane, 1,8-bis(β -epithiopropylthio)-4-(β -epithiopropylthiomethyl)-3,6-dithiaoctane, 1,8-bis(β -epithiopropylthio)-4,5-bis(β -epithiopropylthiomethyl)-3,6-dithiaoctane, 1,8-bis(β -epithiopropylthio)-4,4-bis(β -epithiopropylthiomethyl)-3,6-dithiaoctane, 1,8-bis(β -epithiopropylthio)-2,4,5-tris(β -epithiopropylthiomethyl)-3,6-dithiaoctane, 1,8-bis(β -epithiopropylthio)-2,5-bis(β -epithiopropylthiomethyl)-3,6-dithiaoctane, 1,9-bis(β -epithiopropylthio)-5-(β -epithiopropylthiomethyl)-5-[(2- β -epithiopropylthioethyl)thiomethyl]-3,7-dithianonane, 1,10 bis (β -epithiopropylthio)-5,6-bis[2- β -epithiopropylthioethyl)thio]-3,6,9-trithiadecane, 1,11-bis(β -epithiopropylthio)-4,8-bis(β -epithiopropylthiomethyl)-3,6,9-trithiaundecane, 1,11-bis(β -epithiopropylthio)-5,7-bis(β -epithiopropylthio methyl)-3,6,9-trithiaundecane, 1,11-bis(β -epithiopropylthio)-5,7-[(2- β -epithiopropylthio)thiomethyl]-3,6,9-trithiaundecane and 1,11-bis(β -epithiopropylthio)-4,7-bis(β -epithiopropylthiomethyl)-3,6,9-trithiaundecane ; and compounds obtained by substituting at least one hydrogen atom of the episulfide group in the above compounds with methyl group, cyclic aliphatic organic compounds such as 1,3- and 1,4-bis(β -epithiopropylthio)cyclohexanes, 1,3-and 1,4-bis(β -epithiopropylthiomethyl)cyclohexanes, bis[4-(β -epithiopropylthio)cyclohexyl]methane, 2,2-bis[4-(β -epithiopropylthio)cyclohexyl]propane, bis[4-(β -epithiopropylthio)cyclohexyl] sulfide, 2,5-bis(β -epithiopropylthiomethyl)-

1,4-dithiane and 2,5-bis(β -epithiopropylthioethylthiomethyl)-1,4-dithiane ; and compounds obtained by substituting at least one hydrogen atom of the episulfide group in the above compounds with methyl group and aromatic organic compounds such as 1,3- and 1,4-bis(β -epithiopropylthio)benzenes, 1,3-
 5 and 1,4-bis(β -epithiopropylthiomethyl)benzenes, bis[4-(β -epithiopropylthio)phenyl]methane, 2,2-bis[4-(β -epithiopropylthio)phenyl]propane, bis[4-(β -epithiopropylthio)phenyl] sulfide, bis[4-(β -epithiopropylthio)phenyl]sulfone and 4,4'-bis(β -epithiopropylthio)biphenyl ; and compounds obtained by substituting at least one hydrogen atom of the episulfide group in the above
 10 compounds with methyl group. However, compound (a) is not limited to the above compounds shown as examples. The above compounds may be used singly or as a mixture of two or more compounds.

A most preferred episulfide compound is bis-(β -epithiopropyl)sulfide of formula :

15



These compounds are disclosed in EP 0.921.417.


The polymerizable composition of the invention may include solely a
 20 polymerizable episulfide monomer or a mixture of polymerizable episulfide monomers or it may also optionally include one or more other monomer(s) copolymerizable with the episulfide monomer(s). In particular, it may include one ore more other monomer(s) having two or more functional groups which are reactive with the episulfide group(s) and/or the epoxy group(s) of the
 25 episulfide monomers, a monomer having one or more functional groups which are reactive with the episulfide group(s) and/or the epoxy group(s) of the episulfide monomers and one or more other homopolymerizable functional

groups or a monomer having one homopolymerizable functional group which is reactive with the episulfide and/or the epoxy group.

These other polymerizable monomers, when used in the polymerizable composition of the invention, may represent up to 50% by weight of the total weight of the monomers present in the composition and preferably 20% and more preferably 10% by weight or less of the total weight of the monomers present in the polymerizable composition.


Among these other polymers, there may be cited polythiol monomers having two or more, preferably two or three, thiol functions.


The polythiol monomers can be represented by formula (V) :



in which n' is an integer from 2 to 6 and preferably 2 to 3, and R' is an organic group of valency equal to n' .

Useful polythiol monomers are those disclosed in EP-A-394.495 and US Pat. N°4.775.733 and the polythiols corresponding to the following formulas :





and



5

Among the preferred polythiol monomers there may be cited aliphatic polythiols such as pentaerythritol tetrakis mercaptopropionate. 1-(1'-mercaptoethylthio)-2,3-dimercaptopropane, 1-(2'-mercaptoethylthio)-2,3-dimercaptopropane, 1-(3'-mercaptoethylthio)-2,3 dimercaptopropane, 1-(4'-mercaptoethylthio)-2,3-dimercaptopropane, 1-(5'-mercaptoethylthio)-2,3 dimercapto-propane, 1-(6'-mercaptoethylthio)-2,3- dimercaptopropane, 1,2bis(4'-mercaptoethylthio)-3-mercapto-propane, 1,2-bis(5'-mercaptoethylthio)-3-mercapto-propane, 1,2bis(6'-mercaptoethylthio)-3-mercapto-propane, 1,2,3-tris(mercaptomethylthio)propane, 1,2,3-tris(3'-mercaptoethylthio)propane, 1,2,3-tris(2'-mercaptoethylthio)propane, 1,2,3-tris(4'-mercaptoethylthio)propane, 1,2,3-tris(6'-mercaptoethylthio)propane, methanedithiol, 1,2-ethanedithiol, 1,1-propanedithiol, 1,2-propanedithiol, 1,3-propanedithiol, 2,2-propanedithiol, 1,6-hexanedithiol-1,2,3-propanetrithiol, and 1,2-bis(2'-mercaptoethylthio)-3-mercapto-propane.

20

Preferred polythiol monomers are bis(2,2'-thioethyl)sulfide, 1,2bis(2'-mercaptoethylthio)-3-mercapto-propane and pentaerythritol tetrakis mercaptopropionate.

Among the other monomers, there may also be cited monomers including one or more (meth)acrylate functionalities. Examples of such monomers are benzyl acrylate, benzyl methacrylate, butoxyethyl acrylate, butoxymethyl methacrylate, cyclohexyl acrylate, cyclohexyl methacrylate, 2-

25

- hydroxyethyl acrylate, 2-hydroxyethyl methacrylate, glycidyl acrylate, glycidyl methacrylate, phenoxyethyl acrylate, phenoxyethyl methacrylate, phenyl methacrylate, 3-phenoxy-2-hydroxypropyl acrylate, ethyleneglycol diacrylate, ethyleneglycol dimethacrylate, diethyleneglycol dimethacrylate,
- 5 triethyleneglycol diacrylate, triethyleneglycol dimethacrylate, tetraethyleneglycol diacrylate, tetraethyleneglycol dimethacrylate, polyethyleneglycol diacrylate, polyethyleneglycol dimethacrylate, neopentylglycol diacrylate, neopentylglycol dimethacrylate, ethyleneglycolbisglycidyl diacrylate, ethyleneglycolbisglycidyl
- 10 dimethacrylate, bisphenol-A diacrylate, bisphenol-A dimethacrylate, 2,2-bis(4-acryloxyethoxyphenyl)propane, 2,2-bis(4-methacryloxyethoxyphenyl)propane, 2,2-bis(4-acryloxydiethoxyphenyl)propane, 2,2-bis(4-methacryloxydiethoxy phenyl) propane, bisphenol-F diacrylate, bisphenol-F dimethacrylate, 1,1-bis(4-acryloxyethoxyphenyl)methane, 1,1-bis(4-methacryloxyethoxy phenyl)
- 15 methane, 1,1-bis(4-acryloxydiethoxyphenyl)methane, 1,1-bis(4-methacryloxydiethoxy phenyl)methane, 1,1-bis(4-methacryloxydiethoxyphenyl) methane, dimethyloltricyclodecane diacrylate, trimethylolpropane triacrylate, trimethylolpropane trimethacrylate, glycerol diacrylate, glycerol dimethacrylate, pentaerythritol triacrylate, pentaerythritol tetraacrylate,
- 20 pentaerythritol tetramethacrylate, methylthio acrylate, methylthio methacrylate, phenylthio acrylate, benzylthio methacrylate, xylenedithiol diacrylate, xylenedithiol dimethacrylate, mercaptoethylsulfide diacrylate and mercaptoethylsulfide dimethacrylate ; allyl compounds such as allyl glycidyl ether, diallyl phthalate, diallyl terephthalate, diallyl isophthalate, diallyl
- 25 carbonate and diethyleneglycol-bisallyl carbonate, vinyl compounds such as styrene, chlorostyrene, methylstyrene, bromostyrene, dibromostyrene, divinylbenzene and 3,9-divinyl-spiro-bis-(m-dioxane) ; and diisopropenylbenzene.

A preferred (meth)acrylate monomer is 2-hydroxy-3-phenoxypropyl acrylate.

The polymerizable composition according to the invention may also include additives which are conventionally employed in polymerizable compositions intended for moulding optical articles, in particular ophthalmic lenses, in conventional proportions, namely inhibitors, dyes, UV absorbers, perfumes, deodorants, antioxydants, antiyellowing agents and release agents.

The perfumes allow the odour of the composition to be masked, in particular during surfacing or routing operations.

10 In particular, usual UV absorbers such as those commercialized under the tradenames UV 5411[®], UV 9[®], Tinuvin 400[®], Tinuvin P[®] and Tinuvin 312[®] may be used in amounts generally up to 0.4% by weight of the total polymerizable monomers weight.

Also, the compositions of the invention preferably comprises release agents in an amount up to 0.1% by weight of the total polymerizable monomers weight.

Among the release agents, there may be cited mono and dialkylphosphates, silicones, fluorinated hydrocarbons, fatty acids and ammonium salts. The preferred release agents are mono and dialkylphosphates and mixtures thereof. Such release agents are disclosed inter alia in document 20 US Patent N°4,662,376, US Patent N°4,675,328 and EP-271.839.

The compositions of the present invention are very reactive at room temperature, and a gel can be obtained within a polymerization time of 1 to 60 minutes, usually less than 15 minutes.

25 In the following examples, unless otherwise stated, all the percentages and parts are in weight.

Example 1 and comparative examples C1 and C2

Mixtures containing 9g of bis(β -epithiopropyl)sulfide (component A) and 0,5g of 2-hydroxy-3-phenoxypropylacrylate (component C) were placed in glass vials. To these mixtures, they were added a solution of different catalysts, the solvent and 0,5g of bis(2,2'-thioethyl)sulfide (component B). The mixtures
 5 were stirred magnetically for about 10 seconds and then kept at room temperature without stirring. The polymerized materials have a thickness of about 5 mm and a diameter of about 46 mm.

The nature and quantity of catalyst used, the nature of the solvent and the gel time are reported in Table I.

10

TABLE I

Example N°	Catalyst (ppm)	Solvent	Gel time (minutes)
C1	ϕ_3P (607)	THF	No gel after 1 hour
C2	(4-Me ϕ) $_3P$ (559)	THF	90
1	(4-MeO ϕ) $_3P$ (577)	THF	8

ϕ_3P : Triphenyl phosphine

15 (4-Me ϕ) $_3P$: Tris(4-methylphenyl)phosphine

(4-MeO ϕ) $_3P$: Tris(4-methoxyphenyl)phosphine

Examples 2 to 5

Several experiments were conducted as in example 1 using tris(4-methoxyphenyl) phosphine as catalyst and different percentages of the
 20 components A, B and C in the formulations.

Monomer formulations and gel time are given in Table II below :

TABLE II

Example N°	Monomer Formulation (%)			Catalyst (ppm)	Gel time (minutes)
	A	B	C		
2	99.36	0	0	491	20
3	89.38	4.88	5.21	577	8
4	89.42	5.05	4.91	636	7
5	89.40	4.95	5.04	599	9

5 Examples 6 to 11

Several experiments were carried out as in example 1 using tris(4-methoxyphenyl)phosphine as catalyst and replacing component B by an equivalent weight of pentaerythritol tetrakis mercaptopropionate (component D) or 1,2bis(2'-mercaptoethylthio)-3 mercaptopropane(component E).

The formulations and results are given in Table III :

TABLE III

Example N°	Monomer Formulation (%)					Catalyst (ppm)	Gel time (minutes)
	A	B	C	D	E		
6	88.61	-	4.95	5.65	-	662	13
7	89.22	5.02	4.98	-	-	600	8
8	88.68	-	4.93	5.55	-	573	40
9	89.68	4.51	5.01	-	-	577	13
10	86.19	-	4.98	-	8.19	584	7
11	89.38	4.88	5.21	-	-	577	7

Examples 12 to 17

Plano lenses were molded in plano molds having flat sides. The molds
5 were closed with a tape material. The formulations used contained 36g of component A, 2g of component B, 2g of component C and variable amounts of tris(4-methoxyphenyl)phosphine catalyst dissolved in tetrahydrofuran. The molded lenses were 5mm thick and 85 mm in diameter.

The amounts of catalyst used and the gel times are given in Table IV.

10

TABLE IV

Example N°	Catalyst (ppm)	Gel time (minutes)
12	572	90 < t < 150
13	599	10
14	596	10
15	628	10
16	654	6
17	687	6

Examples 18 to 22

15 2mm thick and 85 mm diameter lenses were molded using plano molds having flat sides from a formulation containing approximately 19.14 g of component A, 1.06g of component B and 1.07g of component C and variable amounts of tris(4-methoxyphenyl)phosphine catalyst disclosed in 1-methyl-2-pyrrolidone (NMP). The molds were closed with a tape material.

20 Catalyst concentrations and resulting gel times are given in Table V.

TABLE V

Example N°	Catalyst (ppm)	Gel time (minutes)
18	589	26
19	602	26
20	705	20
21	904	16
22	1190	12

Surprisingly, as shown by Table V, higher amount of catalyst can be used when molding 2 mm thick plano lenses than 5 mm thick plano lenses without charring.


While not being bound by any theory, it is believed that this result can be explained by the higher value of the ratio surface/volume in the case of the 2mm thick lenses resulting in a higher efficiency of the heat exchange during the exothermic polymerization reaction.

As shown by the examples, episulfide monomer based composition may be fast polymerized at room temperature using (alkoxyphenyl)phosphine catalysts according to the invention.

CLAIMS

1. A polymerizable composition comprising at least one polymerizable monomer having at least one episulfide functionality and an effective amount of
 5 a polymerization catalyst comprising a phosphine having at least one alkoxyphenyl group.

2. The polymerizable composition of claim 1, wherein the polymerization catalyst is selected among phosphines of formula (I):



and mixtures thereof,

in which R and R' are alkyl groups, x is an integer from 1 to 3, y is an integer from 1 to 3, z is an integer from 0 to 2 with the proviso that $x+y=3$, t is
 15 0, 1, 2 or 3.

3. The polymerizable composition as in claim 2, wherein R is selected from $\text{C}_1\text{-C}_6$ alkyl groups.


4. The polymerizable composition as in claim 3, wherein R is CH_3 .

5. The polymerizable composition as in claim 2, wherein $x=3$ and $y=1$.

20 6. The polymerizable composition as in claim 5, wherein the alkoxy group is in position 4 of the phenyl ring.

7. The polymerizable composition as in claim 2, wherein the polymerization catalyst is selected from : tris(3-methoxyphenyl)phosphine, tris(4-methoxyphenyl)phosphine, tris(2,6-dimethoxyphenyl)phosphine and
 25 tris(2,4,6-trimethoxyphenyl)phosphine.

8. The polymerizable composition as in claim 1, wherein the polymerizable monomer having at least one episulfide functionality is a compound having one or more structures represented by the following formula (II) in one molecule :




in which R^1 represents a hydrocarbon group having 1 to 10 carbon atoms, R^2 , R^3 and R^4 each represents a hydrogen atom or a hydrocarbon group having 1 to 10 carbon atoms, X represents S or O with the proviso that in the molecule the average number of S represented by X is about 50% or more of the total number of S and O constituting the three-membered rings.

9. The polymerizable composition as in claim 8, wherein X is S.

10. The polymerizable composition as in claim 8, wherein the compound having one or more structures of formula (II) comprises two structures of formula (II).

11. The polymerizable composition in claim 10, wherein X is S.

12. The polymerizable composition as in claim 1, wherein the polymerizable monomer having at least one episulfide functionality is a compound represented by the formula (III) :



in which R^5 to R^{10} each represents hydrogen atom or a hydrocarbon group having 1 to 10 carbon atoms, X represents S or O with the proviso that in the molecule the average number of S represented by X is about 50% or more of the total number of S and O constituting the three-membered rings, m represents an integer from 0 to 6 and n represents an integer from 0 to 4.

13. The polymerizable composition as in claim 12, wherein X is S.

14. The polymerizable composition as in claim 12, wherein the polymerizable monomer having at least one episulfide functionality is bis(β -epithiopropyl)sulfide.

15. The polymerizable composition as in claim 1 further comprising at least one other monomer copolymerizable with the episulfide monomer.

16. The polymerizable composition as in claim 15, wherein said other polymerizable monomer is a polythiol having two or more thiol functions.

17. The polymerizable composition as in claim 16, wherein the polythiol compound is bis(2,2'-thioethyl)sulfide, pentaerythritol tetrakis mercaptopropionate or 1,2 bis(2'-mercaptoethylthio)-3 mercaptopropane.

18. The polymerizable composition as in claim 15, wherein the said other copolymerizable monomer is a monomer having one or more (meth)acrylate functionalities.

19. The polymerization composition as in claim 18, wherein said other monomer is 2-hydroxy-3-phenoxypropylacrylate.

20. The polymerizable composition as in claim 15, wherein said other copolymerizable monomer represents 10% by weight or less of the total weight of the polymerizable monomers present in the composition.


21. A cast optical article made of a polymerized composition as set forth in claim 1.

22. An ophthalmic lens made of a polymerized composition as set forth in claim 1.

23. The cast optical article of claim 21 having a refractive index of at least 1.7.

24. The ophthalmic lens of claim 22 having a refractive index of at least 1.7.

5 25. A process for fast polymerization at room temperature of a composition comprising at least one polymerizable monomer having at least one episulfide functionality which comprises adding to the composition an effective amount of a catalyst selected from phosphines of formula (I):



10

and mixtures thereof,

in which R and R' are alkyl groups, x is an integer from 1 to 3 and y is an integer from 1 to 3, z is an integer from 0 to 2 with the proviso that $x+y=3$.

15 26. The process of claim 25, wherein the polymerization catalyst is selected from tris(4-methoxyphenyl)phosphine, tris(2,6-dimethoxyphenyl)phosphine and tris(2,4,6-trimethoxyphenyl)phosphine.

27. The process of claim 25, wherein the polymerization catalyst is tris(4-methoxyphenyl)-phosphine.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
28 March 2002 (28.03.2002)

PCT

(10) International Publication Number
WO 02/024786 A3

(51) International Patent Classification⁷: C08G 75/00, 75/08, G02B 1/04

(21) International Application Number: PCT/EP01/11021

(22) International Filing Date:
24 September 2001 (24.09.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
09/669,099 25 September 2000 (25.09.2000) US

(71) Applicant (*for all designated States except US*): ES-SILOR INTERNATIONAL COMPAGNIE GENERALE D'OPTIQUE [FR/FR]; 147 rue de Paris, F-94227 CHARENTON cedex (FR).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): JALLOULI, Aref, Ben, Ahmed, [TN/US]; 13433 104th Avenue N., LARGO, FL 33774 (US). KEITA, Gabriel [FR/US]; 394 Fountain View Circle, OLDSMAR, FL 34677 (US). WEBER, Steve [US/US]; 14045 Egreet Line, CLEARWATER, FL 33762 (US). TURSHANI, Yassin [US/US]; 8073 Somerset Drive, LARGO, FL 33773 (US).

(74) Agents: CATHERINE, Alain et al.; Cabinet HARLE et PHELIP, 7 rue de Madrid, F-75008 PARIS (FR).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

(88) Date of publication of the international search report:
4 July 2002

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: EPISULFIDE BASED POLYMERIZABLE COMPOSITION CATALYZED BY AN (ALKOXYPHENYL)PHOSPHINE

(57) Abstract: The room temperature polymerizable composition comprises at least one polymerizable monomer having at least one episulfide functionality and an effective amount of at least one (alkoxyphenyl)phosphine polymerization catalyst.



WO 02/024786 A3

INTERNATIONAL SEARCH REPORT

Int. Application No.

PCT/EP 01/11021

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08G75/00 C08G75/08 G02B1/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08G G02B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 1 024 223 A (MITSUBISHI GAS CHEMICAL CO) 2 August 2000 (2000-08-02) page 20; example 70	1-27
A	DE 18 14 640 A (ETHYLENE-PLASTIQUE) 31 July 1969 (1969-07-31) examples 1-11	1-27
A	GB 893 314 A (ILFORD LTD) 4 April 1962 (1962-04-04) example 12; table 1 column 1, line 40 - line 43	1-27
A	GB 1 077 958 A (ICI LTD) 2 August 1967 (1967-08-02) example 1	1-27
	--- -/--	

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *8* document member of the same patent family

Date of the actual completion of the international search

22 April 2002

Date of mailing of the international search report

07/05/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

O'Sullivan, T

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 01/11021

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 442 568 A (SHELL INT RESEARCH) 21 August 1991 (1991-08-21) claim 1 -----	1-27

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 01/11021

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 1024223	A	02-08-2000	EP 1024223 A2	02-08-2000
			JP 2000281787 A	10-10-2000
			US 6365223 B1	02-04-2002
			JP 2000345480 A	12-12-2000
DE 1814640	A	31-07-1969	BE 724123 A	02-05-1969
			DE 1814640 A1	31-07-1969
			FR 1591837 A	04-05-1970
			GB 1167079 A	15-10-1969
			NL 6817933 A	17-06-1969
			US 3644302 A	22-02-1972
GB 893314	A	04-04-1962	NL 121699 C	
			NL 260337 A	
GB 1077958	A	02-08-1967	NONE	
EP 0442568	A	21-08-1991	JP 2767310 B2	18-06-1998
			JP 3239718 A	25-10-1991
			CA 2036414 A1	17-08-1991
			DE 69115074 D1	18-01-1996
			DE 69115074 T2	29-08-1996
			EP 0442568 A2	21-08-1991
			ES 2080232 T3	01-02-1996
			US 5089543 A	18-02-1992